



MW13 Mill Wound Steel Strapping

Product data

~ surface finish	black painted and waxed, deburred edges
~ winding	oscillated
~ strap width	12.7 mm
~ width tolerance	+/- 0.15 mm
~ strap thickness	0.5 mm
~ thickness tolerance	+/- 0.03 mm
~ strap length on coil	1010 mtr
~ coil inside diameter	406 mm
~ coil outside diameter	600 mm (approx.)
~ coil weight	50 kg (approx.)
~ coils per pallet	12

Technical data

~ tensile strength (minimum)	800 N/mm ²
~ tensile strength (average)	900 N/mm ²
~ breaking strain (minimum)	5080 N
~ breaking strain (average)	5710 N
~ elongation, A5 (average)	7.0%
~ elongation, A100 (minimum)	1.0%
~ elongation, A100 (average)	2.5%

All information and recommendations are provided to the best of our knowledge, on the basis of our practical experience. Nevertheless we can make no warranties, expressed or implied, including but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is therefore responsible for determining whether the product is fit for a particular purpose and suitable for the user's method of application.